# QuikPlastik

# PLASTIC REPAIR EPOXY PUTTY STICK

REPAIRS ANYTHING MADE OF ABS, CPVC, AND PVC PLASTIC

# Rebuild...

Rigid and semi-flexible plastics

# Repair...

- Automotive trim
- Appliance parts
- PVC furniture
- Vinyl siding
- Plastic downspouts and gutters


# Seal...

 Leaks in PVC and ABS plastic plumbing pipes


- The ultimate solution for small or emergency repairs
- Easy-to-use and mistake-proof
- Bonds instantly with superior strength

uik**Plastik**°

- Saves hundreds of dollars in repairs
- Belongs in every toolbox









Made in U.S.A.

**MINUTE** WORK LIFE

# QuikPlastik Plastic Repair Epoxy Putty Stick

#### **Product Description**

QuikPlastik is a hand-mixable, fast-setting epoxy putty that forms a durable bond to most major plastic types\*. After mixing it forms a polymer compound that can be molded, wrapped around, or used to build up and repair just about anything made from rigid or semi-flexible plastic. After 2 to 3 hours it can be sawed, drilled, carved, sanded, and painted. Each handy stick contains pre-measured portions of activator and base throughout — no measuring or mixing tools are necessary. The consistency (like modeling clay) eliminates drips and runs, molds easily, and facilitates adhesion to the substrate. Suitable for interior or exterior use, it is resistant to water, chemicals, and temperature extremes. QuikPlastik contains no solvents or VOCs. It's non-flammable and releases no noxious fumes. It won't shrink or pull away. The unused portion stays fresh for future use when saved in its original package.

\* Does not adhere to polyethylene, polypropylene or some other plastics. Test for adhesion

#### Performance Data\*

SHELF LIFE AT 75°F (24°C) SHORE D HARDNESS AT FULL CURE (24 hrs) LAP SHEAR TENSILE STRENGTH On PVC (1" x 1" x 1/16")

**COMPRESSIVE STRENGTH DENSITY SHRINKAGE NON-VOLATILE CONTENT ELECTRICAL RESISTANCE** DIELECTRIC STRENGTH **TEMPERATURE LIMITS** 

> Continuous Intermittent

24 months minimum

350 lbs (2.5 MPa)

8,000 psi (55 MPa) 13.4 lb/gal (1.6 gm/cm<sup>3</sup>) 100% 30,000 megohms-cm 300 volts/mil

-40° to 250°F (-40° to 121°C) -40° to 300°F (-40° to 149°C)

#### CHEMICAL RESISTANCE

Resistant to hydrocarbons, ketones, alcohols, esters, halocarbons, aqueous salt solutions and dilute acids and bases.

NOT INTENDED FOR STRUCTURAL APPLICATIONS

\*Not to be used for specification purposes.

## **Applicable Standards**

Certified by NSF International to NSF/ANSI Standard 61 for drinking water contact.

Labeling conforms to ASTM D-4236.


## Availability

QuikPlastik is one in a family of Specialty Epoxy Putties originated and manufactured by

Polymeric Systems, Inc. Also look for QuikAluminum, QuikCopper, RepairitQuik, FastSteel, AquaMend, InstaCrete, QuikWood, and QuikTitanium. Our epoxy putties give you the ability to fix just about anything.

#### Packaging Options

QuikPlastik is available in 3.5" (2 oz) and 7" (4 oz) lengths, individually packaged in a reusable clear plastic tube with trilingual (English, Spanish, French) instructions and plastic friction top. The display carton holds 12 or 24 - 3.5" sticks or 12 - 7" sticks (packed 2 display





Pop-Up Cardboard Display Carton



Packs



Acrvlic Display Racks

#### **How To Use**

Before applying, roughen and clean the area to be repaired. Wear impervious gloves when mixing or handling uncured QuikPlastik. Then follow these easy steps.







Mixed Color **OFF-WHITE** 

- 1. Cut or twist off required amount 2. Mix by kneading with gloved fingers to a uniform color. If mixing is difficult, warm QuikPlastik to room temperature or slightly above.
- 3. Apply to surface to be repaired within 10 minutes of mixing. Force into any cracks or holes, and extend the patch at least 1 inch beyond the area being repaired.

When applying to a damp, wet or slowly leaking area, work the mixed material forcefully into the surface and apply pressure until adhesion begins to take effect.

For best results: Use damp fingers for easier mixing, application, and a smooth appearance of the cured compound. Remove excess material before hardening begins.

Curing: QuikPlastik has a 20- to 25-minute work life. Functional cure occurs in 2 to 3 hours.

Contains Epoxy Resin and Tri (dimethylaminomethyl) phenol. Skin and eye irritant/sensitizer. Direct product contact may cause allergic reaction in some individuals. Wear impervious gloves when mixing or handling uncured product. Avoid contact with eyes. • Inhalation of dust may be harmful; wear dust mask and protective eyewear when sanding cured product. Ingestion of product may be harmful. KEEP OUT OF REACH OF CHILDREN. See product insert or SDS for additional information.

> Polymeric Systems, Inc., is a part of Whitford Worldwide. For more information, please contact Polymeric Systems or Whitford Ltd. at:

Polymeric Systems, Inc. 47 Park Avenue Elverson, PA 19520 888-EPOXY FIX (888-376-9934) Tel: +[1] (610) 286-2500 Email: sales@polymericsystems.com Website: polymericsystems.com

In the EU contact: Whitford Ltd. 11 Stuart Road, Manor Park Runcorn, Cheshire, UK WA7 1TH Tel: +[44] (0) 1928 571000 Email: salesuk@whitfordww.com Website: whitfordww.com

NON-WARRANTY: ALL RECOMMENDATIONS, STATEMENTS AND TECHNICAL DATA CONTAINED HEREIN ARE BASED ON TESTS WE BELIEVE TO BE RELIABLE AND CORRECT, BUT ACCURACY AND COMPLETENESS OF SAID TESTS ARE NOT GUARANTEED AND ARE NOT TO BE CONSTRUED AS A WARRANTY, EITHER EXPRESS OR IMPLIED. USER SHALL RELY ON HIS OWN INFORMATION AND TESTS TO DETERMINE SUITABILITY OF THE PRODUCT FOR THE INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY RESULTING FROM THIS USE OF THE PRODUCT. MANUFACTURER'S SOLE RESPONSIBILITY SHALL BE TO REPLACE THAT PORTION OF THE PRODUCT OF THE MANUFACTURER THAT PROVES TO BE DEFECTIVE. MANUFACTURER SHALL NOT BE LIABLE TO THE BUYER OR ANY THIRD PARTY FOR INJURY, LOSS OR DAMAGE DIRECTLY OR INDIRECTLY RESULTING FROM USE OF, OR INABILITY TO USE, THE PRODUCT. RECOMMENDATIONS OR STATEMENTS OTHER THAN THOSE CONTAINED IN A WRITTEN AGREEMENT SIGNED BY AN OFFICER OF THE MANUFACTURER SHALL NOT BE BINDING UPON THE MANUFACTURER.

4023-0213 © Polymeric Systems, Inc. 2013